

Gripsure Pro Premier Specification

Slip resistance

Gripsure Pro Premier decking profile using two inserts will achieve a minimum PTV value of 94 (pendulum test value) Gripsure Pro Premier decking using three inserts will achieve a minimum PTV value of 100. Gripsure non slip decking has been independently tested using the pendulum test (the operation and calibration of which are described in BS7976:2002 parts 1 and 3) operated to the United Kingdom Slip Resistance Group (UKSRG).

Aggregate inserts

Gripsure Pro Premier decking uses a 0.5mm - 1.4mm double washed and screened Guyanan Calcined Bauxite – grey colour with a minimum PSV (polished stone value) of 70.

Timber board

Gripsure Pro Premier uses slow grown Northern European fifth grade redwood. Growth rings will be seen to be closer together when comparing with home grown or faster grown products. The close grain offers excellent working properties for machining to profile and is much less liable to splitting or cracking. In addition, the moisture content and cell structure of redwood allows for better penetration of preservative treatment.

Gripsure Pro Premier is supplied with FSC® timber – Certificate No TT-COC-003864.

Gripsure Pro Premier board profile dimensions are ex 150mm width x 38mm depth, giving a finished product profile of approx 145mm x 32mm. Standard lengths available are 2.4m to 5.1m. A bespoke cutting service is available for any lengths.

Gripsure Pro Premier is vacuum/pressure treated to meet the requirements of Use Class 4 (BS EN 335), and visually graded to a minimum of C16, which gives 25 year in service life.

Maintenance

Gripsure Pro Premier is a low maintenance product, no further preservative treatment is necessary. The green/brown colour finish will fade over time to a lighter sun bleached finish.

Gripsure Pro Premier can be stained or painted, or water repellent sealant can be applied every 12 months to give extra protection to the timber.

Gripsure Pro Premier is pressure washable – it is recommended to remove dirt and mould build up across the surface of the board and inserts every 12 months, using a 150bar water pressure washer with fan nozzle at a minimum distance of 150mm.

Cross cut components

Any cuts, notches or drill holes to Gripsure Pro Premier decking during construction must be treated with end-grain preservative to maintain the integrity of the timber treatment, and the 25 year in service life.

Contact us for more information

 01726 844616  info@gripsure.co.uk  www.gripsure.co.uk

Unit 2, Rockhill Business Park, Bugle Cornwall PL26 8RA